

TECHNICAL DATA SHEET



Magic of Additive...

MAA DURGA POLYCHEM

We Understands Your Needs...

MDPC-ONE PACK P.V.C HEAT STABILIZER

Product Information

MDPO 6000 is a high purity, non-wettable, **MDPO** 6000 powder/flakes manufactured with high quality stearic acid, Stearates and the Additives. During manufacturing, the particle size, shape, bulk density, and purity of **MDPO** 6000 are closely controlled to guarantee product uniformity.

- High performance.
- No odour during processing and in the final product.
- Cost efficient.
- No solubility in water, no leaking into the environment.
- Quality controlled.

TYPICAL PROPERTIES

Description	Specifications
Appearance	White Flakes
Lead Content (as PbO)	42+1%
Free Fatty Acid	0.5% max.
Specific Gravity	1.50-1.55
Moisture	0.3% max.

TECHNICAL DATA SHEET

RECOMMENDATIONS FOR APPLICATION

MDPC 6000 are mainly recommended for extrusion of rigid pipes, pressure & non pressure pipes, casing & capping etc. **MDPC** 6000 are well balanced complex lead stabilizers with internal and external lubricants. Economy and efficacy are the major features of this lead based one pack stabilizer. Lubricants are specially designed to provide external stability during the process.

EASY HANDLING

Eliminates bridging or caking while facilitating use in any type of packaging, bulk handling or conveying system.

DOSAGE

Wires/Cables/Pipe – 1.25 – 1.75 phr

PACKAGING:

25 Kg. Bag.

No warranty, expressed or implied, or merchantability, fitness for a particular purpose or otherwise is made, except that the products herein discussed comply with the chemical description on the labels. Buyer assumes risks of the use, storage and handling. Hummel shall not be liable for any incidental or consequential damages arising directly or indirectly in connection with the purchase, use, storage or handling of this product. The information contained herein is, to the best of our knowledge, true and accurate. However, all recommendation or suggestions are made without guarantee, since the conditions of use are beyond our control. We disclaim any liability incurred in connection with the use of these data or suggestions. This information is not to be taken as a license to operate under, or a recommendation to infringe any patent (s).
--

R157, Street No. : 14A, Swatantra Nagar, Narela, Delhi-110040, India

Phone no. : +91 9811941073, +91 9811941076

E-mail ID: info@maadurgapolychem.com

E-mail ID: maadurgapolychem@rediffmail.com